

Elcometer 122 Testex® Replica Tape

Elcometer 122 Testex® Tape consists of foam with a non-compressible backing.

The foam side is rubbed into the surface providing a permanent mould of the peak-to-valley profile, which can then be measured using the Elcometer 124 Thickness Gauge.

Elcometer 122 Testex® Tape is available in four profile ranges. It is important that the tape grade chosen is reflective of the profile being measured.

- For profiles between 12 & 25µm (0.5 & 1.0mils): Coarse Minus Tape
- For profiles between 20 & 38µm (0.8 & 1.5mils): Coarse Tape
- For profiles between 38 & 64µm (1.5 & 2.5mils): Average of Coarse and X-Coarse Tape
- For profiles between 64 & 115µm (2.5 & 4.5mils): X-Coarse Tape
- For profiles greater than 115µm (4.5mils): X-Coarse Plus Tape

There are 50 tests in each roll.



STANDARDS:

ASTM D 4417-C, BS 7079-C5, ISO 8503-5, NACE RP0287, SSPC PA 17, US Navy NSI 009-32, US Navy PPI 63101-000


Technical Specification

Description	Profile Range		Part Number			
	Metric	Imperial	1 Roll	Pack of 10	Pack of 50	Pack of 100
Elcometer 122 Coarse Minus	12 - 25µm	0.5 - 1.0mils	E122----A1	E122----A10	E122----A50	E122----A100
Elcometer 122 Coarse	20 - 64µm	0.8 - 2.5mils	E122----B1	E122----B10	E122----B50	E122----B100
Elcometer 122 X-Coarse	38 - 115µm	1.5 - 4.5mils	E122----C1	E122----C10	E122----C50	E122----C100
Elcometer 122 X-Coarse Plus	116 - 127µm	4.6 - 5.0mils	E122----F1	E122----F10	E122----F50	E122----F100


Accessories

T12222498	Swizzle Sticks (Pack of 5)
-----------	----------------------------


How to take a reading using the Testex® Replica Tape




1. Tear off one section of the tape from the roll, peel off the backing tape and retain the back if required for future use.




2. Stick the tape on to the test surface, and rub the central portion using the swizzle stick provided, or the end of a pen, pencil or similar rounded object until dark spots appear. This gives a surface replica.



3. Using a micrometer such as the Elcometer 124 Foil Thickness Gauge, measure the thickness of the central portion of the tape replica and subtract 50µm (2mils) from the reading. This result is the peak-to-valley profile height. Write the value on the tape.



4. If the value falls within the purple band on the coarse tape (38-64µm) then repeat the test as shown in step 2 using the extra coarse tape and then average the two values.



5. If the tape is required for future reference, replace the backing tape to preserve the imprinted profile.

نماینده فروش در ایران

کاوشکاران

تلفن: ۰۲۱ - ۸۸۶۸ ۵۲۹۷

www.IR-QC.com